

TECHNICAL DATA SHEET OF RECLAIM RUBBER KRPL-202 (MEDIUM RECLAIM RUBBER)

CHEMICAL PROPERTIES

TECHNICAL DATA SPECIFICATION	TEST METHOD	KRPL-202 (MEDIUM RECLAIM RUBBER)
ACETONE EXTRACT (%)	ASTM D 297-18	14+4
ASH CONTENT (%)	ASTM D 297-18	10 Max
CARBON BLACK (%)	ASTM E1131	25+2
VOLATILE MATTER (%)		1.0(Max)
RHC (%)	ASTM E1131	50(Min)

PHYSICAL PROPERTIES

SPECIFIC GRAVITY (gm/cc)	ASTM D 297-18	1.14±0.03
TENSILE STRENGTH(Kg/cm ²)	ASTM D 412	45(Min)
ELONGATION (%)	ASTM D 412	210 Min
HARDNESS AT SHORE "A"	ASTM D 2240	57±5
MOONEY VISCOSITY(1+4@100°C)	ASTM D 1646	25-55

**LAKHOWAL ROAD, NEAR KOHARA CHOWK,
KOHARA LAKHOWAL LINK ROAD, PUNJAB-141112**

PHONE NO: +91 9501190521, +91 9417035614